



SEAJET BIOCLEAN ECO

Product description

SEAJET BIOCLEAN ECO is a biocide-free, silicone foul-release coating for use on underwater hulls. Provides long term protection against fouling in both fresh and salt water environments. Fouling may loosely attach but is easily removed by water movement or washing (sponge).

Product data

Colour	Clear
Flash point	56°C
Volume solids %	94 ±2
VOC (Theoretical)	51 g/l.
Pack sizes	0.75lt, 2.5lt
Mixing ratio	One pack product

Application details

Thinner	SEAJET THINNER A	
Application methods	Brush, roller, airless spray (please consult Seajet Department first)*	
Conditions	Ambient temperature	min. 5°C - max. 35°C
	Max. humidity	85% R.H.
	Product temperature	min. 5°C - max. 35°C
	Substrate temperature	min. 7°C - max. 35°C
Spray details	Nozzle tip	Graco 619, 719
	Paint output pressure:	17.7 - 20.6 MPa
	Thinning:	0 - 1 % (by volume)
Spreading rate	10,0	m ² /l (theoretical)
Recommended film thickness per coat	Wet (µm)	100
	Dry (µm)	94
Substrates	For use over suitably primed GRP, wood, steel, aluminium.	
Preceding coating	SEAJET TIE COAT	
Subsequent coating	SEAJET BIOCLEAN ECO	
Mixing	Before use, stir thoroughly until product is mixed to a uniform consistency.	

Notes	<p>Warning: Due to the presence of silicon compounds, contamination of other areas by e.g. overspray should be avoided. This can result in failure in those areas.</p> <p>Brushes, rollers and spray lines should be dedicated or be thrown away. Mask areas close by to avoid overspray.</p> <p>For the expectations of performance from this foul-release coating in static conditions: It is necessary to consider parameters such as trading pattern and the environmental conditions i.e., traditional level of fouling activity, pollution levels and water temperatures at static locations.</p> <p>*In case of brush or roller application, more layers will be required to achieve the specified film thickness. Values are based on roller application.</p>
-------	---

Surface preparation

New application: Apply 2 coats of SEAJET BIOCLEAN ECO (using a thick mohair roller) over freshly applied SEAJET TIE COAT.

Re-coat of BIOCLEAN ECO in good condition: Clean the existing surface with low pressure fresh water. Use a soft sponge to remove any fouling which is more difficult to remove.

After cleaning rinse the hull with fresh water and let it dry. When the surface is dry apply two fresh coats of SEAJET BIOCLEAN ECO using a thick mohair roller.

Re-coat of BIOCLEAN ECO in bad condition: Clean the existing surface with low pressure fresh water. Use a soft sponge to remove any fouling which is more difficult to remove.

Repair the damaged areas by using a paint scraper to remove the existing SEAJET BIOCLEAN ECO. Use abrasive paper (P-100) to roughen the SEAJET TIE coat. Apply a fresh coat of SEAJET TIE coat.

After repair rinse the hull with fresh water and let it dry. When the surface is dry apply two fresh coats of SEAJET BIOCLEAN ECO using a mohair roller.



SEAJET BIOCLEAN ECO

Drying / overcoating data

Temperature	Drying time (at DFT 100 µ)	Overcoating interval (at DFT 100 µ)	Induction time	Pot life	Dry to launch	Remarks
5 °C	Surface dry: 50 min Hard dry: 8 hours	Min.: 8 hours Max.: None	-	-	1 day	-
10 °C	Surface dry: 40 min Hard dry: 6 hours	Min.: 6 hours Max.: None	-	-	1 day	-
20 °C	Surface dry: 30 min Hard dry: 5 hours	Min.: 5 hours Max.: None	-	-	1 day	-
30 °C	Surface dry: 20 min Hard dry: 4 hours	Min.: 4 hours Max.: None	-	-	1 day	-

Notes: Drying times and overcoating intervals will increase with increasing film thickness applied.
Before re-coating, always check that the existing paint film is 'through' dry.

General information

Storage

Store the containers in a dry, cool and well ventilated space and away from direct sunlight. Containers must be kept firmly closed. Handle with care.

Transportation

The product should stay in a securely closed container during transport.

Shelf life

Min. 2 years @ 20°C

Disposal

Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point.

Additional information

More information can be found on www.seajetpaint.com.

Safety information

Personal Protection advice and additional information can be obtained from the product Safety Data Sheet from Chugoku Paints B.V. which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist and vapours.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Disclaimer

Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam. Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.