

Epifanes PU Speedcoat Colour

A professional topcoat finish for spray applications



PRODUCT DESCRIPTION

A professional two-component high gloss finish with outstanding flowing properties. Dedicated to spray application with extremely short overcoating times. Provides long lasting gloss retention and is scratch - and weather resistant. After full cure polishable.

Field of use: Solely for spray application on GRP / Steel / Aluminium / Plywood. Protecting and ecstatic finish for interior and exterior use in combination with the correct priming system. This product is **not** suited for brush/roller applications.

PRODUCT INFORMATION

Type	Chemical drying
Base	Acrylic poly-ol
Gloss	Extreme high gloss
Colours	On request: Epifanes colours, maritime related colours and RAL colours
Density at 20°C.	1,10 - 1,30 g/cm³ depending on colour
Viscosity	40 seconds ISO-cup 4 mm
Solids Contents	40 ± 2 vol. % by volume - 50 ± 2 vol. % by weight
VOC-level after mix	569 g/l
Packing	2 kg. Component A + 1 kg. Component B. = 3 kg
Shelf life	In closed unopened container stored in a dry room at temperatures between 5 - 30°C Component A: 3 years after production date - Component B: 1 year after production date
Mixing ratio by weight	2 parts base component A : 1 part curing component B
Mixing instructions	Well stir base component A prior to adding curing component B. Stir both components together for at least 5 minutes to a homogeneous substance. (2 minutes with mechanical stirring).
Thinner	Slow : Epifanes PU Speedcoat Spraythinner Fast : Epifanes Poly-urethane Spray Thinner
Thinning guideline	Add thinner after mixing both components. Thinning ratio depends on product temperature and working area. Avoid overthinning.
Induction time 20°C.	10 minutes
Rec. film thickness	60 - 70 µm wet = 30 - 35 µm dry

Drying times	15°C.	20°C.	25°C.
Dust dry	1.5 hours	1 hour	1 hour
Recoatable	2 hours	1 hour	1 hour
Sandable	30 hours	24 hours	20 hours
Potlife after mixing	4 hours	3 hours	1.5 hours

The above mentioned drying times are indicative at 65% RAH and 35 µm dry film thickness. Drying also depends on the amount of ventilation and applied wet film thickness. Higher wet film thickness and/or limited ventilation result in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness.

Substrate conditions Well cured, cleaned, degreased, sanded, intact two component paint systems. In new systems, build up with Epifanes Epoxy Primers and Epifanes Poly-urethane Primer.
Polishing: After 1 week at 20°C.



Epifanes PU Speedcoat Colour

A professional topcoat finish for spray applications

APPLICATION

Conditions during application **Temperature** minimal 15°C. - maximal 30°C.
Relative air humidity minimal 50% - maximal 75%

This product is dedicated to spray application by conventional air, HVLP and RP spray guns. Finest results however are achieved by RP gun. Evenly distribute the coating on the surface. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid large difference in temperature of the product, surface to be coated and working area. Wet-on-wet application is possible when the solvents have evaporated. When applying a subsequent coat after 48 hours, always sand.

Guidelines for spray application:

	Thinning volume	Nozzle	Pressure	Visco DIN-cup 4 mm
Air / HLVP spray	15-20%	1.2 mm - 1.6 mm	2.5 – 3.5 Bar	17 - 20 seconds
RP spray	15-20%	1.1 mm - 1.3 mm	2.2 – 2.5 Bar	17 - 20 seconds

Application remarks Airless spray not advised. Pressure feed paint container: Pot life will be shortened due to temperature increase in the container. Before spraying, check filter house and filters on contamination.

Theoretical coverage 12m² per kg. @ 30 µm dry film thickness
Practicle coverage Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatibility wet-on-wet With itself after 60-90 minutes @ 20°C.

Recoatibility For additional gloss and depth one or more coats Epifanes PU Speedcoat Clear Gloss may be applied on top of Epifanes PU Speedcoat Colour. This is also recommended in case of polishing.

Polishing After 7 days @ 20°C.

Intercoat sanding Not required (wet-on-wet application.)
 Only sand if subsequent coat is applied after 48 hours @ 20°C.

System build up

Amount of coats	3 coats or more
Film thickness per coat wet	60 - 80 µm wft
Film thickness per coat dry	30 - 40 µm dft
Total film thickness	90 - 120 µm dft

Safety The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV
 PO box 166
 1430 AD Aalsmeer
 Netherlands
 Phone +31 297 – 360366
 info@epifanes.nl
 www.epifanes.nl

